

Reference Only

Spec. No. JENF243A-9101V-01

P.1/10

Chip Ferrite Bead BLM18□□□□□□H1D Murata Standard Reference Specification[AEC-Q200]

1.Scope

This reference specification applies to Chip Ferrite Bead for Automotive Electronics BLM18_□H Series based on AEC-Q200.

2.Part Numbering

(ex.) BL M 18 AG 121 S H 1 D
 (1) Product ID (2) Type (3) Dimension (L×W) (4) Characteristics (5) Typical Impedance at 100MHz (6) Performance (7) Category(for Automotive Electronics) (8) Numbers of Circuit (9) Packaging (D:Taping)

3.Rating

| Customer Part Number | MURATA Part Number | Impedance (Ω) (at 100MHz)(*1) (refer to below comment) | | Rated Current (mA) | | DC Resistance (Ω max.) (*1) (refer to below comment) | | Remark | ESD Rank 2:2kV 6:25kV |
|----------------------|--------------------|--|------|--------------------|----------|---|----------------------|----------------------------------|-----------------------------|
| | | Typical | | at 85°C | at 125°C | Initial Values | Values After Testing | | |
| | BLM18PG300SH1D | 20 min. | 30 | 1000 | | 0.05 | 0.10 | For DC power line | 6 |
| | BLM18PG330SH1D | 33±25% | 33 | 3000*2 | 1000*2 | 0.025 | 0.050 | | |
| | BLM18PG600SH1D | 40 min. | 60 | 1000 | | 0.1 | 0.2 | | |
| | BLM18PG121SH1D | 120±25% | 120 | 2000*2 | 1000*2 | 0.05 | 0.10 | | |
| | BLM18PG181SH1D | 180±25% | 180 | 1500*2 | 1000*2 | 0.09 | 0.18 | | |
| | BLM18PG221SH1D | 220±25% | 220 | 1400*2 | 1000*2 | 0.10 | 0.14 | | |
| | BLM18PG331SH1D | 330±25% | 330 | 1200*2 | 1000*2 | 0.15 | 0.20 | | |
| | BLM18PG471SH1D | 470±25% | 470 | 1000 | | 0.20 | 0.26 | | |
| | BLM18SP300SH1D | 30±10 | 30 | 6000*2 | 4000*2 | 0.008 | 0.010 | | |
| | BLM18SP101SH1D | 100±25% | 100 | 3700*2 | 2500*2 | 0.022 | 0.026 | | |
| | BLM18SP221SH1D | 220±25% | 220 | 2800*2 | 1900*2 | 0.040 | 0.048 | | |
| | BLM18SP601SH1D | 600±25% | 600 | 1500*2 | 1000*2 | 0.140 | 0.168 | | |
| | BLM18SP102SH1D | 1000±25% | 1000 | 1200*2 | 800*2 | 0.185 | 0.222 | | |
| | BLM18KG221SH1D | 220±25% | 220 | 2200*2 | 1500*2 | 0.050 | 0.060 | | |
| | BLM18KG331SH1D | 330±25% | 330 | 1700*2 | 1200*2 | 0.080 | 0.095 | 2 | |
| | BLM18KG471SH1D | 470±25% | 470 | 1500*2 | 1000*2 | 0.130 | 0.145 | | |
| | BLM18KG601SH1D | 600±25% | 600 | 1300*2 | 1000*2 | 0.150 | 0.165 | | |
| | BLM18KG102SH1D | 1000±25% | 1000 | 1000*2 | 800*2 | 0.200 | 0.230 | | |
| | BLM18SN220TH1D | 22±7 | 22 | 8000*2 | 5000*2 | 0.004 | 0.005 | For DC power line (Thin type) | 2 |
| | BLM18KG260TH1D | 26±25% | 26 | 6000*2 | 4000*2 | 0.007 | 0.012 | | |
| | BLM18KG300TH1D | 30±25% | 30 | 5000*2 | 3300*2 | 0.010 | 0.015 | | |
| | BLM18KG700TH1D | 70±25% | 70 | 3500*2 | 2200*2 | 0.022 | 0.032 | | |
| | BLM18KG101TH1D | 100±25% | 100 | 3000*2 | 1900*2 | 0.030 | 0.040 | | |
| | BLM18KG121TH1D | 120±25% | 120 | 3000*2 | 1900*2 | 0.030 | 0.040 | | |
| | BLM18AG121SH1D | 120±25% | 120 | 800 | | 0.18 | 0.28 | For general use | 2 |
| | BLM18AG151SH1D | 150±25% | 150 | 700 | | 0.25 | 0.35 | | |
| | BLM18AG221SH1D | 220±25% | 220 | 700 | | 0.25 | 0.35 | | |
| | BLM18AG331SH1D | 330±25% | 330 | 600 | | 0.30 | 0.40 | | |
| | BLM18AG471SH1D | 470±25% | 470 | 550 | | 0.35 | 0.45 | | |
| | BLM18AG601SH1D | 600±25% | 600 | 500 | | 0.38 | 0.48 | | |
| | BLM18AG102SH1D | 1000±25% | 1000 | 450 | | 0.50 | 0.60 | | |

Reference Only

Spec. No. JENF243A-9101V-01

P.2/10

| Customer Part Number | MURATA Part Number | Impedance (Ω) (at 100MHz)(*1) (refer to below comment) | Rated Current (mA) | | DC Resistance (Ω max.) (*1) (refer to below comment) | | Remark | ESD Rank 2:2kV 6:25kV | |
|----------------------|--------------------|--|--------------------|---------|---|----------------|----------------------------|-----------------------------|----------------------|
| | | | Typical | at 85°C | at 125°C | Initial Values | | | Values After Testing |
| | | | | | | | | | |
| | BLM18BB050SH1D | 5±25% | 5 | 800 | 0.05 | 0.10 | For high speed signal line | 2 | |
| | BLM18BA050SH1D | 5±25% | 5 | 500 | 0.2 | 0.3 | | | |
| | BLM18BB100SH1D | 10±25% | 10 | 700 | 0.10 | 0.20 | | | |
| | BLM18BA100SH1D | 10±25% | 10 | 500 | 0.25 | 0.35 | | | |
| | BLM18BB220SH1D | 22±25% | 22 | 700 | 0.20 | 0.30 | | | |
| | BLM18BA220SH1D | 22±25% | 22 | 500 | 0.35 | 0.45 | | | |
| | BLM18BB470SH1D | 47±25% | 47 | 600 | 0.25 | 0.35 | | | |
| | BLM18BD470SH1D | 47±25% | 47 | 500 | 0.3 | 0.4 | | | |
| | BLM18BA470SH1D | 47±25% | 47 | 300 | 0.55 | 0.65 | For high speed signal line | 2 | |
| | BLM18BB600SH1D | 60±25% | 60 | 600 | 0.25 | 0.35 | | | |
| | BLM18BA750SH1D | 75±25% | 75 | 300 | 0.70 | 0.80 | | | |
| | BLM18BB750SH1D | 75±25% | 75 | 600 | 0.30 | 0.40 | | | |
| | BLM18BB121SH1D | 120±25% | 120 | 550 | 0.30 | 0.40 | | | |
| | BLM18BD121SH1D | 120±25% | 120 | 300 | 0.4 | 0.5 | | | |
| | BLM18BA121SH1D | 120±25% | 120 | 200 | 0.9 | 1.0 | | | |
| | BLM18BB141SH1D | 140±25% | 140 | 500 | 0.35 | 0.45 | | | |
| | BLM18BB151SH1D | 150±25% | 150 | 450 | 0.37 | 0.47 | | | |
| | BLM18BD151SH1D | 150±25% | 150 | 300 | 0.4 | 0.5 | | | |
| | BLM18BB221SH1D | 220±25% | 220 | 450 | 0.45 | 0.55 | | | |
| | BLM18BD221SH1D | 220±25% | 220 | 250 | 0.45 | 0.55 | | | |
| | BLM18BB331SH1D | 330±25% | 330 | 400 | 0.58 | 0.68 | | | |
| | BLM18BD331SH1D | 330±25% | 330 | 250 | 0.5 | 0.6 | | | |
| | BLM18BD421SH1D | 420±25% | 420 | 250 | 0.55 | 0.65 | | | |
| | BLM18BB471SH1D | 470±25% | 470 | 300 | 0.85 | 0.95 | | | |
| | BLM18BD471SH1D | 470±25% | 470 | 250 | 0.55 | 0.65 | | | |
| | BLM18BD601SH1D | 600±25% | 600 | 200 | 0.65 | 0.75 | | | |
| | BLM18BD102SH1D | 1000±25% | 1000 | 200 | 0.85 | 0.95 | | | |
| | BLM18BD152SH1D | 1500±25% | 1500 | 150 | 1.2 | 1.3 | | | |
| | BLM18BD182SH1D | 1800±25% | 1800 | 150 | 1.5 | 1.6 | | | |
| | BLM18BD222SH1D | 2200±25% | 2200 | 150 | 1.5 | 1.6 | | | |
| | BLM18BD252SH1D | 2500±25% | 2500 | 150 | 1.5 | 1.6 | | | |

• Operating Temperature : -55°C to +125°C (*1)

• Storage Temperature : -55°C to +125°C

Standard Testing Conditions


< Unless otherwise specified >

Temperature : Ordinary Temp. (15 °C to 35 °C)
Humidity : Ordinary Humidity (25%(RH) to 85%(RH))

< In case of doubt >



Temperature : 20°C±2 °C
Humidity : 60%(RH) to 70%(RH)
Atmospheric pressure : 86kPa to 106kPa

(Note)As for Rated current marked with *2,
Rated Current is derated as right figure
depending on the operating temperature.



Reference Only

4. Style and Dimensions



: Electrode

■ Equivalent Circuit



(Resistance element becomes dominant at high frequencies.)

■ Unit Mass (Typical value)

BLM18_SH : 0.005g

BLM18_TH : 0.004g

| P/N | T |
|----------|----------|
| BLM18_SH | 0.8±0.15 |
| BLM18_TH | 0.6±0.15 |

(in mm)

5. Marking

No marking.

6. Specifications

6-1. Electrical Performance

| No. | Item | Specification | Test Method |
|-------|---------------|---------------|--|
| 6-1-1 | Impedance | Meet item 3. | Measuring Frequency : 100MHz±1MHz Measuring Equipment : KEYSIGHT 4991A or the equivalent Test Fixture : KEYSIGHT 16192A or the equivalent |
| 6-1-2 | DC Resistance | Meet item 3. | Measuring Equipment : Digital multi meter For BLM18SN Measuring Equipment : YOKOGAWA 755611 or the equivalent Test Fixture : KEYSIGHT 16044A or the equivalent * Except resistance of the Substrate and Wire |

6-2. Mechanical Performance (based on Table 13 for FILTER EMI SUPPRESSORS/FILTERS)

AEC-Q200 Rev.D issued June. 1 2010

| AEC-Q200 | | | Murata Specification / Deviation | | | | | | |
|------------------------------|---|--|--|------------|-----------|------------------------------|---|---------------|--------------|
| No. | Stress | Test Method | | | | | | | |
| 3 | High Temperature Exposure | 1000hours at 125 deg C Set for 24hours at room temperature, then measured. | Meet Table A after testing. <u>Table A</u> <table border="1" style="margin-left: 20px;"> <tr> <td>Appearance</td> <td>No damage</td> </tr> <tr> <td>Impedance Change (at 100MHz)</td> <td>Within ±30% (for BLM18SN Within ±50%)</td> </tr> <tr> <td>DC Resistance</td> <td>Meet item 3.</td> </tr> </table> | Appearance | No damage | Impedance Change (at 100MHz) | Within ±30% (for BLM18SN Within ±50%) | DC Resistance | Meet item 3. |
| Appearance | No damage | | | | | | | | |
| Impedance Change (at 100MHz) | Within ±30% (for BLM18SN Within ±50%) | | | | | | | | |
| DC Resistance | Meet item 3. | | | | | | | | |
| 4 | Temperature Cycling | 1000cycles -55 deg C to +125 deg C Set for 24hours at room temperature, then measured. | Meet Table B after testing. <u>Table B</u> <table border="1" style="margin-left: 20px;"> <tr> <td>Appearance</td> <td>No damage</td> </tr> <tr> <td>Impedance Change (at 100MHz)</td> <td>Within ±30% (for BLM18SN Within ±50%) (for BLM18KG Within -10%to+50%)</td> </tr> <tr> <td>DC Resistance</td> <td>Meet item 3.</td> </tr> </table> | Appearance | No damage | Impedance Change (at 100MHz) | Within ±30% (for BLM18SN Within ±50%) (for BLM18KG Within -10%to+50%) | DC Resistance | Meet item 3. |
| Appearance | No damage | | | | | | | | |
| Impedance Change (at 100MHz) | Within ±30% (for BLM18SN Within ±50%) (for BLM18KG Within -10%to+50%) | | | | | | | | |
| DC Resistance | Meet item 3. | | | | | | | | |

Reference Only

Spec. No. JENF243A-9101V-01

P.4/10


| AEC-Q200 | | | Murata Specification / Deviation | | | | | | |
|------------------------------|---|---|--|------------|-----------|------------------------------|---|---------------|--------------|
| No. | Stress | Test Method | | | | | | | |
| 5 | Destructive Physical Analysis | Per EIA469 No electrical tests | No defects | | | | | | |
| 7 | Biased Humidity | 1000hours at 85 deg C, 85%RH Apply max rated current. | Meet Table C after testing. <u>Table C</u> <table border="1" style="margin-left: auto; margin-right: auto; border-collapse: collapse;"> <tr> <td style="padding: 2px;">Appearance</td> <td style="padding: 2px;">No damage</td> </tr> <tr> <td style="padding: 2px;">Impedance Change (at 100MHz)</td> <td style="padding: 2px;">Within $\pm 30\%$ (for BLM18KG/SN Within $\pm 50\%$)</td> </tr> <tr> <td style="padding: 2px;">DC Resistance</td> <td style="padding: 2px;">Meet item 3.</td> </tr> </table> | Appearance | No damage | Impedance Change (at 100MHz) | Within $\pm 30\%$ (for BLM18KG/SN Within $\pm 50\%$) | DC Resistance | Meet item 3. |
| Appearance | No damage | | | | | | | | |
| Impedance Change (at 100MHz) | Within $\pm 30\%$ (for BLM18KG/SN Within $\pm 50\%$) | | | | | | | | |
| DC Resistance | Meet item 3. | | | | | | | | |
| 8 | Operational Life | Apply 125 deg C 1000hours Set for 24hours at room temperature, then measured | Meet Table C after testing. If the rated current of parts exceed 1A, the operating temperature should be 85 deg C. | | | | | | |
| 9 | External Visual | Visual inspection | No abnormalities | | | | | | |
| 10 | Physical Dimension | Meet ITEM 4 (Style and Dimensions) | No defects | | | | | | |
| 12 | Resistance to Solvents | Per MIL-STD-202 Method 215 | Not Applicable | | | | | | |
| 13 | Mechanical Shock | Per MIL-STD-202 Method 213 Condition F 1500g's (14.7N)/0.5ms/ Half sine | Meet Table D after testing. <u>Table D</u> <table border="1" style="margin-left: auto; margin-right: auto; border-collapse: collapse;"> <tr> <td style="padding: 2px;">Appearance</td> <td style="padding: 2px;">No damage</td> </tr> <tr> <td style="padding: 2px;">Impedance Change (at 100MHz)</td> <td style="padding: 2px;">Within $\pm 30\%$</td> </tr> <tr> <td style="padding: 2px;">DC Resistance</td> <td style="padding: 2px;">Meet item 3.</td> </tr> </table> | Appearance | No damage | Impedance Change (at 100MHz) | Within $\pm 30\%$ | DC Resistance | Meet item 3. |
| Appearance | No damage | | | | | | | | |
| Impedance Change (at 100MHz) | Within $\pm 30\%$ | | | | | | | | |
| DC Resistance | Meet item 3. | | | | | | | | |
| 14 | Vibration | 5g's(0.049N) for 20 minutes, 12cycles each of 3 orientations Test from 10-2000Hz. | Meet Table D after testing. | | | | | | |
| 15 | Resistance to Soldering Heat | Solder temperature 260C+/-5 deg C Immersion time 10s | Pre-heating: 150C +/-10 deg,60s to 90s Meet Table C after testing. | | | | | | |
| 17 | ESD | Per AEC-Q200-002 | Meet Table D after testing. ESD Rank: Meet Item 3. (Rating) | | | | | | |
| 18 | Solderability | Per J-STD-002 | Method b : Not Applicable 95% of the terminations is to be soldered. | | | | | | |
| 19 | Electrical Characterization | Measured : Impedance | No defects | | | | | | |
| 20 | Flammability | Per UL-94 | Not Applicable | | | | | | |
| 21 | Board Flex | Epoxy-PCB(1.6mm) Deflection 2mm(min) 60s minimum holding tim | Meet Table C after testing. | | | | | | |
| 22 | Terminal Strength | Per AEC-Q200-006 | No defects | | | | | | |
| 30 | Electrical Transient Conduction | Per ISO-7637-2 | Not Applicable | | | | | | |

(5) Outside package


These reels shall be packed in the corrugated cardboard package and the following items shall be marked on a label and the label is stuck on the box.

(Customer name, Purchasing order number, Customer part number, MURATA part number, RoHS discrimination(*2), Quantity, etc)

(6) Dimensions of reel and taping (leader-tape, trailer-tape)



7-4. Specification of Outer Case



| Outer Case Dimensions (mm) | | | Standard Reel Quantity in Outer Case (Reel) |
|----------------------------|-----|----|---|
| W | D | H | |
| 186 | 186 | 93 | 5 |

* Above Outer Case size is typical. It depends on a quantity of an order.

8. Caution

8-1. Rating

Do not use products beyond the Operating Temperature Range and Rated Current.

8-2. Surge current

Excessive surge current (pulse current or rush current) than specified rated current applied to the product may cause a critical failure, such as an open circuit, burnout caused by excessive temperature rise.

Please contact us in advance in case of applying the surge current.

8-3. Fail Safe

Be sure to provide an appropriate fail-safe function on your product to prevent from a second damage that may be caused by the abnormal function or the failure of our products.

8-4. Limitation of Applications

Please contact us before using our products for the applications listed below which require especially high reliability for the prevention of defects which might directly cause damage to the third party's life, body or property.

- | | |
|-----------------------------------|--|
| (1) Aircraft equipment | (6) Disaster prevention / crime prevention equipment |
| (2) Aerospace equipment | (7) Traffic signal equipment |
| (3) Undersea equipment | (8) Transportation equipment (trains, ships, etc.) |
| (4) Power plant control equipment | (9) Data-processing equipment |
| (5) Medical equipment | (10) Applications of similar complexity and /or reliability requirements to the applications listed in the above |

8-5. Corrosive gas

Please refrain from use since contact with environments with corrosive gases (sulfur gas [hydrogen sulfide, sulfur dioxide, etc.], chlorine, ammonia, etc.) or oils (cutting oil, silicone oil, etc.) that have come into contact with the previously stated corrosive gas environment will result in deterioration of product quality or an open from deterioration due to corrosion of product electrode, etc. We will not bear any responsibility for use under these environments.


9. Notice

This product is designed for solder mounting.

Please consult us in advance for applying other mounting method such as conductive adhesive.

9-1. Land pattern designing


< For BLM18 series (except BLM18P/BLM18S/BLM18K type) >



| Type | Soldering | a | b | c |
|------------------------------------|-----------|-----|-----|-----|
| BLM18 (except 18P/18S/BLM18K type) | Flow | 0.8 | 2.5 | 0.7 |
| | Reflow | 0.7 | 2.0 | 0.7 |

(in mm)

< For BLM18P/BLM18S/BLM18K type >



| Type | Rated Current (A) | Soldering | a | b | c | Land pad thickness and dimension d | | |
|------------------|-------------------|-----------------|------------------------------|------------------------------|-----|------------------------------------|------|------|
| | | | | | | 18μm | 35μm | 70μm |
| BLM18P BLM18K | 0.5 to 1.5 | Flow/ Reflow | Flow 0.8 Reflow 0.7 | Flow 2.5 Reflow 2.0 | 0.7 | 0.7 | 0.7 | 0.7 |
| | 1.7 to 2.5 | | | | | 1.2 | 0.7 | 0.7 |
| | 3 to 4 | | | | | 2.4 | 1.2 | 0.7 |
| | 5 to 6 | | | | | 6.4 | 3.3 | 1.65 |
| BLM18SN | 8 | | | | | - | 6.4 | 3.3 |
| BLM18SP | 1.2 to 6.0 | | | | | - | 6.4 | - |

(in mm)

*The excessive heat by land pads may cause deterioration at joint of products with substrate.

9-2. Soldering Conditions

Products can be applied to reflow and flow soldering.

(1) Flux, Solder

| | |
|--------|--|
| Flux | Use rosin-based flux, but not highly acidic flux (with chlorine content exceeding 0.2(wt)%.) Do not use water-soluble flux. |
| Solder | Use Sn-3.0Ag-0.5Cu solder Standard thickness of solder paste : 100 μm to 200 μm |

(2) Soldering conditions

- Pre-heating should be in such a way that the temperature difference between solder and ferrite surface is limited to 150°C max. Also cooling into solvent after soldering should be in such a way that the temperature difference is limited to 100°C max.


Insufficient pre-heating may cause cracks on the ferrite, resulting in the deterioration of product quality.

- Standard soldering profile and the limit soldering profile is as follows.

The excessive limit soldering conditions may cause leaching of the electrode and / or resulting in the deterioration of product quality.


(3)soldering profile

Flow soldering profile



| | Standard Profile | Limit Profile |
|---------------|------------------|-------------------|
| Pre-heating | 150°C、60s min. | |
| Heating | 250°C、4~6s | 265°C±3°C、5s max. |
| Cycle of flow | 2 times | 2 times |

Reflow soldering profile



| | Standard Profile | Limit Profile |
|------------------|---------------------|----------------------|
| Pre-heating | 150~180°C、90s±30s | |
| Heating | above 220°C、30s~60s | above 230°C、60s max. |
| Peak temperature | 245±3°C | 260°C、10s |
| Cycle of reflow | 2 times | 2 times |


9-3.Reworking with soldering iron

- Pre-heating: 150°C, 1 min
- Tip temperature: 350°C max.
- Soldering time : 3(+1,-0) seconds.
- Soldering iron output: 80W max.
- Tip diameter: φ 3mm max.
- Times : 2times max.

Note :Do not directly touch the products with the tip of the soldering iron in order to prevent the crack on the ferrite material due to the thermal shock.

9-4.Solder Volume

Solder shall be used not to be exceeded as shown below.



$$\frac{1}{3}T \leq t \leq T$$

(T:Chip thickness)


Accordingly increasing the solder volume, the mechanical stress to product is also increased. Exceeding solder volume may cause the failure of mechanical or electrical performance.

9-5.Attention regarding P.C.B. bending

The following shall be considered when designing and laying out P.C.B.'s.

(1) P.C.B. shall be designed so that products are not subject to the mechanical stress for board warpage.

<Products direction>




Products shall be located in the sideways direction (Length: $a < b$) to the mechanical stress.

(2)Components location on P.C.B. separation.

It is effective to implement the following measures, to reduce stress in separating the board.

It is best to implement all of the following three measures; however, implement as many measures as possible to reduce stress.


| Contents of Measures | Stress Level |
|--|--------------|
| (1) Turn the mounting direction of the component parallel to the board separation surface. | $A > D *1$ |
| (2) Add slits in the board separation part. | $A > B$ |
| (3) Keep the mounting position of the component away from the board separation surface. | $A > C$ |



*1 $A > D$ is valid when stress is added vertically to the perforation as with Hand Separation.
If a Cutting Disc is used, stress will be diagonal to the PCB, therefore $A > D$ is invalid.

(3) Mounting Components Near Screw Holes

When a component is mounted near a screw hole, it may be affected by the board deflection that occurs during the tightening of the screw. Mount the component in a position as far away from the screw holes as possible.



9-6.Mounting density

Add special attention to radiating heat of products when mounting the inductor near the products with heating.

The excessive heat by other products may cause deterioration at joint of this product with substrate.

9-7. Operating Environment

Do not use this product under the following environmental conditions, on deterioration of the Insulation Resistance of the Ferrite material and/or corrosion of Inner Electrode may result from the use.

- (1) in the corrodible atmosphere such as acidic gases, alkaline gases, chlorine, sulfur gases, organic gases and etc. (the sea breeze, Cl_2 , H_2S , NH_3 , SO_2 , NO_2 , etc)
- (2) in the atmosphere where liquid such as organic solvent, may splash on the products.
- (3) in the atmosphere where the temperature / humidity changes rapidly and it is easy to dew.

9-8. Resin coating

The impedance value may change and/or it may affect on the product's performance due to high cure-stress of resin to be used for coating / molding products. So please pay your careful attention when you select resin. In prior to use, please make the reliability evaluation with the product mounted in your application set.