FG Series



Overview

FG Series Supercapacitors, also known as Electric Double-Layer Capacitors (EDLCs), are intended for high energy storage applications.

Applications

Supercapacitors have characteristics ranging from traditional capacitors and batteries. As a result, supercapacitors can be used like a secondary battery when applied in a DC circuit. These devices are best suited for use in low voltage DC hold-up applications such as embedded microprocessor systems with flash memory.

Benefits

- Wide range of temperature from -25°C to +70°C (FG and FGH types) and -40°C to +85°C (FGR type)
- · Maintenance free
- Maximum operating voltages of 3.5 VDC and 5.5 VDC
- · Highly reliable against liquid leakage
- · Lead-free and RoHS compliant




Part Number System

FG	0H	104	Z	F
Series	Maximum Operating Voltage Capacitance Code		Capacitance Tolerance	Environmental
FG FGH FGR	0V = 3.5 VDC 0H = 5.5 VDC	First two digits represent significant figures. Third digit specifies number of zeros to follow µF code.	Z = -20/+80%	F = Lead-free



Dimensions - Millimeters



Part Number	ø D	Н	P	ę	d ₁	d ₂
FG0H103ZF	11.0	5.5	5.08	2.7	0.2	1.2
FG0H223ZF	11.0	5.5	5.08	2.7	0.2	1.2
FG0H473ZF	11.0	5.5	5.08	2.7	0.2	1.2
FG0H104ZF	11.0	6.5	5.08	2.7	0.2	1.2
FG0H224ZF	13.0	9.0	5.08	2.2	0.4	1.2
FG0H474ZF	14.5	18.0	5.08	2.4	0.4	1.2
FG0H105ZF	16.5	19.0	5.08	2.7	0.4	1.2
FG0H225ZF	21.5	19.0	7.62	3.0	0.6	1.2
FG0H475ZF	28.5	22.0	10.16	6.1	0.6	1.4
FG0V155ZF	16.5	14.0	5.08	3.1	0.4	1.2
FGH0H104ZF	11.0	5.5	5.08	2.7	0.2	1.2
FGH0H224ZF	11.0	7.0	5.08	2.7	0.2	1.2
FGH0H474ZF	16.5	8.0	5.08	2.7	0.4	1.2
FGH0H105ZF	21.5	9.5	7.62	3.0	0.6	1.2
FGH0V474ZF	13.0	7.5	5.08	2.7	0.4	1.2
FGR0H474ZF	14.5	18.0	5.08	2.4	0.4	1.2
FGR0H105ZF	16.5	19.0	5.08	2.7	0.4	1.2
FGR0H225ZF	21.5	19.0	7.62	3.0	0.6	1.2



Performance Characteristics

Supercapacitors should not be used for applications such as ripple absorption because of their high internal resistance (several hundred $m\Omega$ to a hundred Ω) compared to aluminum electrolytic capacitors. Thus, its main use would be similar to that of secondary battery such as power back-up in DC circuit. The following list shows the characteristics of supercapacitors as compared to aluminum electrolytic capacitors for power back-up and secondary batteries.

	Seconda	ry Battery	Сара	citor
	NiCd	Lithium Ion	Aluminum Electrolytic	Supercapacitor
Back-up ability	-	-	-	-
Eco-hazard	Cd	-	-	-
Operating Temperature Range	-20 to +60°C	-20 to +50°C	-55 to +105°C	-40 to +85°C (FR, FT, FMR type)
Charge Time	Few hours	Few hours	Few seconds	Few seconds
Charge/Discharge Life Time	Approximately 500 times	Approximately 500 to 1,000 times	Limitless (*1)	Limitless (*1)
Restrictions on Charge/Discharge	Yes	Yes	None	None
Flow Soldering	Not applicable	Not applicable	Applicable	Applicable
Automatic Mounting	Not applicable	Not applicable	Applicable	Applicable (FM and FC series)
Safety Risks	Leakage, explosion	Leakage, combustion, explosion, ignition	Heat-up, explosion	Gas emission (*2)

^(*1) Aluminum electrolytic capacitors and supercapacitors have limited lifetime. However, when used under proper conditions, both can operate within a predetermined lifetime.

Typical Applications

Intended Use (Guideline)	Power Supply (Guideline)	Application	Examples of Equipment	Series
Long time back-up	500 μA and below	CMOS microcomputer, IC for clocks	CMOS microcomputer, static RAM/DTS (digital tuning system)	FG series

^(*2) There is no harm as it is a mere leak of water vapor which transitioned from water contained in the electrolyte (diluted sulfuric acid). However, application of abnormal voltage surge exceeding maximum operating voltage may result in leakage and explosion.



Environmental Compliance

All KEMET supercapacitors are RoHS compliant.



Table 1 - Ratings & Part Number Reference

Part Number	Maximum Operating	Maximui		Maximum ESR	Maximum Current at 30	Voltage Holding Characteristic		
Part Number	Voltage (VDC)	Charge System (F)	Discharge System (F)	at 1 kHz (Ω)	Minutes (mA)	Minimum (V)	Weight (g)	
FG0V155ZF	3.5	1.5	2.2	65	1.5	-	5.2	
FG0H103ZF	5.5	0.010	0.013	300	0.015	4.2	0.9	
FG0H223ZF	5.5	0.022	0.028	200	0.033	4.2	1.0	
FG0H473ZF	5.5	0.047	0.060	200	0.071	4.2	1.0	
FG0H104ZF	5.5	0.10	0.13	100	0.15	4.2	1.3	
FGH0H104ZF	5.5	_	0.10	100	0.15	4.2	1.0	
FG0H224ZF	5.5	0.22	0.28	100	0.33	4.2	2.5	
FGH0H224ZF	5.5	_	0.22	100	0.33	4.2	1.3	
FGH0H105ZF	5.5	_	1.0	35	1.5	4.2	7.2	
FGH0H474ZF	5.5	_	0.47	65	0.71	4.2	4.1	
FGH0V474ZF	3.5	-	0.47	25	0.42	-	2.6	
FG0H474ZF	5.5	0.47	0.60	120	0.71	4.2	5.1	
FGR0H474ZF	5.5	0.47	0.60	120	0.71	4.2	5.1	
FG0H105ZF	5.5	1.0	1.3	65	1.5	4.2	7.0	
FGR0H105ZF	5.5	1.0	1.3	65	1.5	4.2	7.0	
FG0H225ZF	5.5	2.2	2.8	35	3.3	4.2	12.1	
FGR0H225ZF	5.5	2.2	2.8	35	3.3	4.2	12.1	
FG0H475ZF	5.5	4.7	6.0	35	7.1	4.2	27.3	

Part numbers in bold type represent popularly purchased components.



Specifications

Item		FG, FGH Type			FGR Type	Test Conditions (conforming to JIS C 5160-1)			
Category Temperature Range Maximum Operating Voltage		-25°C to		-40°C to +85°C					
Maximum Operating Voltage		5.5 VDC, 3.5 VDC		5.5 VDC	,				
Capacitance		Refer to	Table 1	Refer to	Table 1	Refer to "Measurem	ent Conditions"		
Capacitance Allov	pacitance Allowance		20%	+80%,-2	20%	Refer to "Measurem	ent Conditions"		
ESR		Refer to	Table 1	Refer to	Table 1	Measured at 1 kHz, "Measurement Cond			
Current (30 minute	urrent (30 minutes value)		Table 1	Refer to	Table 1	Refer to "Measurem	ent Conditions"		
	Capacitance	> 90% o	f initial ratings	> 90% o	f initial ratings		6.3 V (5.5 V type) 4.0 V (3.5 V type) 30 seconds 9 minutes 30 seconds 1,000		
Surge	ESR	≤ 120% (of initial ratings	≤ 120%	of initial ratings	Series resistance:	$\begin{array}{ccc} 0.010 \; F & & 1,500 \; \Omega \\ 0.022 \; F & & 560 \; \Omega \\ 0.047 \; F & & 300 \; \Omega \\ 0.10 \; F & & 150 \; \Omega \end{array}$		
	Current (30 minutes value)	≤ 120% (of initial ratings	≤ 120% of initial ratings		Discharge	0.22 F 56 Ω 0.47 F 30 Ω 1.0 F, 1.5 F 15 Ω 2.2 F, 4.7 F 10 Ω		
	Appearance	No obvi	ous abnormality	No obvious abnormality		resistance: Temperature:	0 Ω 70±2°C (FG, FGH) 85±2°C (FGR)		
	Capacitance	Phase 2	e initial value Phase in	≥ 50% of initial value	Conforms to 4.17 Phase 1:	+25±2°C			
	ESR		≤ 400% of initial value	2	≤ 400% of initial value	Phase 2:	-25±2°C -40±2°C (FGR) +25±2°C +70±2°C (FG, FGH) +85±2°C (FGR) +25±2°C		
	Capacitance	Phase 3		Phase 3	≥ 30% of				
	ESR				initial value ≤ 700% of				
	Canasitanas		≤ 200% of		initial value ≤ 200% of	Phase 6:			
Characteristics	Capacitance	-	initial value Satisfy initial	_	initial value Satisfy initial				
in Different Temperature	Current (30 minutes value)	Phase 5	ratings ≤ 1.5 CV (mA)	Phase 5	ratings ≤ 1.5 CV (mA)				
	Capacitance		Within ±20% of		Within ±20% of				
	ESR	Phase	initial value Satisfy initial	Phase	initial value Satisfy initial				
	Current (30 minutes value)	6	ratings Satisfy initial ratings	6	ratings Satisfy initial ratings				
	Capacitance					Conforms to 4.13			
Vibration Resistance	ESR Current (30 minutes value)	Satisfy i	initial ratings	Satisfy initial ratings		Frequency: Testing Time:			
	Appearance	No obvi	ous abnormality	No obvi	ous abnormality				
Solderability		Over 3/4 of the terminal should be covered by the new solder		Over 3/4 of the terminal should be covered by the new solder		Conforms to 4.11 Solder temp: Dipping time:			




Specifications cont.

Ite	em	FG, FGH Type	FGR Type	Test Conditions (conforming to JIS C 5160-1)			
	Capacitance			Conforms to 4.10 Solder temp:	+260±10°C		
Solder Heat Resistance	Current (30 minutes value)	Satisfy initial ratings	Satisfy initial ratings	Dipping time:			
	Appearance	No obvious abnormality	No obvious abnormality	1.6 mm from the bot	tom should be dipped.		
Temperature Cycle	Capacitance			Conforms to 4.12 Temperature	Minimum Annua and		
	ESR	Satisfy initial ratings	Satisfy initial ratings	Condition:	Minimum temperature » Room temperature		
	Current (30 minutes value)				» Category maximum temperature » Room temperature		
	Appearance	No obvious abnormality	No obvious abnormality	Number of cycles: 5 cycles			
High Temperature and High Humidity Resistance	Capacitance	Within ±20% of initial value	Conforms to 4.14				
	ESR	≤ 120% of initial ratings	≤ 120% of initial ratings	Temperature: Relative humidity:	+40±2°C 90 to 95% RH		
	Current (30 minutes value)	≤ 120% of initial ratings	≤ 120% of initial ratings	Testing time:			
	Appearance	No obvious abnormality	No obvious abnormality				
	Capacitance	Within ±30% of initial value	Within ±30% of initial value	Conforms to 4.15 Temperature:	Category maximum		
High	ESR	< 200% of initial ratings	< 200% of initial ratings	Voltage applied:	temperature ±2°C Maximum operating		
Temperature Load	Current (30 minutes value)	< 200% of initial ratings	< 200% of initial ratings	Series protection resistance:	voltage 0 Ω		
	Appearance	No obvious abnormality	No obvious abnormality	Testing time:	1,000+48 (+48/-0) hours		
Self Discharge Characteristics (Voltage Holding Characteristics)		5.5 V type: Voltage between terminal		Charging condition Voltage applied: Series resistance: Charging time:	5.0 VDC (Terminal at the case side must be negative) 0 Ω 24 hours		
		leads > 4.2 V 3.5 V type: Not specified	Voltage between terminal leads > 4.2 V	Storage Let stand for 24 hours in condition describe below with terminals opened.			
				Ambient temperature: Relative humidity:			



Marking



Packaging Quantities


Part Number	Bulk Quantity per Box
FG0H103ZF	2,000 pieces
FG0H223ZF	2,000 pieces
FG0H473ZF	2,000 pieces
FG0H104ZF	1,600 pieces
FG0H224ZF	800 pieces
FG0H474ZF	300 pieces
FG0H105ZF	240 pieces
FG0H225ZF	90 pieces
FG0H475ZF	50 pieces
FG0V155ZF	160 pieces
FGH0H104ZF	2,000 pieces
FGH0H224ZF	1,600 pieces
FGH0H474ZF	600 pieces
FGH0H105ZF	90 pieces
FGH0V474ZF	800 pieces
FGR0H474ZF	300 pieces
FGR0H105ZF	240 pieces
FGR0H225ZF	90 pieces




Measurement Conditions

Capacitance (Charge System)

Capacitance is calculated from expression (9) by measuring the charge time constant (τ) of the capacitor (C). Prior to measurement, the capacitor is discharged by shorting both pins of the device for at least 30 minutes. In addition, use the polarity indicator on the device to determine correct orientation of capacitor for charging.





Eo: 3.0 (V) Product with maximum operating voltage of 3.5 V

5.0 (V) Product with maximum operating voltage of 5.5 V

6.0 (V) Product with maximum operating voltage of 6.5 V

10.0 (V) Product with maximum operating voltage of 11 V $\,$

12.0 (V) Product with maximum operating voltage of 12 V

 τ : Time from start of charging until Vc becomes 0.632 Eo (V)

(seconds)

Rc: See table below (Ω) .

Charge Resistor Selection Guide

Charge Re	Charge Resistor Selection Guide												
Сар	FA	FE	FS	FYD	Y FYH	FR	FM, FME FMR	FMC	FG, FGR	FGH	FT	FC, FCS	HV
0.010 F	_	_	_	_	-	_	5,000 Ω	_	5,000 Ω	-	-	_	-
0.022 F	1,000 Ω	_	1,000 Ω	2,000 Ω	2,000 Ω	2,000 Ω	2,000 Ω	-	2,000 Ω	-	_	Discharge	-
0.033 F	-	-	-	-	_	_	Discharge	-	-	-	-	-	-
0.047 F	1,000 Ω	1,000 Ω	1,000 Ω	2,000 Ω	1,000 Ω	1,000 Ω	2000 Ω	1,000 Ω	2,000 Ω	-	-	-	-
0.10 F	510 Ω	510 Ω	510 Ω	1,000 Ω	510 Ω	1,000 Ω	1000 Ω	1,000 Ω	1,000 Ω	Discharge	510 Ω	Discharge	-
0.22 F	200 Ω	200 Ω	200 Ω	510 Ω	510 Ω	510 Ω	0H: Discharge 0V: 1000 Ω	-	1,000 Ω	Discharge	200 Ω	Discharge	-
0.33 F	_	_	_	-	-	_	_	Discharge	-	-	_	-	-
0.47 F	100 Ω	100 Ω	100 Ω	200 Ω	200 Ω	200 Ω	_	-	1,000 Ω	Discharge	100 Ω	Discharge	-
1.0 F	51 Ω	51 Ω	100 Ω	100 Ω	100 Ω	100 Ω	_	-	510 Ω	Discharge	100 Ω	Discharge	Discharge
1.4 F	_	_	_	200 Ω	-	_	_	-	-	-	_	-	-
1.5 F	_	51 Ω	_	_	_	_	_	-	510 Ω	-	_	_	-
2.2 F	_	_	_	100 Ω	_	_	_	-	200 Ω	-	51 Ω	_	-
2.7 F	_	_	_	_	_	_	_	-	-	-	_	_	Discharge
3.3 F	_	_	_	-	-	_	_	-	-	-	51 Ω	-	-
4.7 F	-	-	-	-	_	_	-	-	100 Ω	-	-	-	Discharge
5.0 F	-	-	100 Ω	-	_	_	-	-	-	-	-	-	-
5.6 F	-	-	-	-	_	_	-	-	-	-	20 Ω	-	-
10.0 F	-	-	-	-	_	_	-	-	-	-	-	-	Discharge
22.0 F	_	_	_	_	-	-	_	-	-	-	_	_	Discharge
50.0 F	_	_	_	_	-	-	_	-	-	-	_	_	Discharge
100.0 F	_	_	_	_	-	-	_	-	-	-	_	_	Discharge
200.0 F	_	-	-	-	_	_	_	-	-	-	_	-	Discharge

^{*}Capacitance values according to the constant current discharge method.

^{*}HV Series capacitance is measured by discharge system.





Measurement Conditions cont.


Capacitance (Discharge System)

As shown in the diagram below, charging is performed for a duration of 30 minutes once the voltage of the capacitor terminal reaches 5.5 V. Then, use a constant current load device and measure the time for the terminal voltage to drop from 3.0 to 2.5 V upon discharge at 0.22 mA per 0.22 F, for example, and calculate the static capacitance according to the equation shown below.

Note: The current value is 1 mA discharged per 1 F.









Capacitance (Discharge System - 3.5 V, 3.6 V)

As shown in the diagram below, charging is performed for a duration of 30 minutes once the voltage of the capacitor terminal reaches 3.5 V (3.6 V). Then, use a constant current load device and measure the time for the terminal voltage to drop from 1.8 to 1.5 V upon discharge at 1.0 mA per 1.0 F, for example, and calculate the static capacitance according to the equation shown below.

$$C = \frac{I \times (T_2 - T_1)}{V_1 - V_2} \ (F)$$







Capacitance (Discharge System - HV Series)

As shown in the diagram below, charging is performed for a duration of 30 minutes once the voltage of the capacitor terminal reaches maximum operating voltage. Then, use a constant current load device and measure the time for the terminal voltage to drop from 2.0 to 1.5 V upon discharge at 1.0 mA per 1.0 F, and calculate the static capacitance according to the equation shown below.

$$C = \frac{I \times (T_2 - T_1)}{V_1 - V_2} \ (F)$$








Measurement Conditions cont.

Equivalent Series Resistance (ESR)

ESR shall be calculated from the equation below.

Current (at 30 minutes after charging)

Current shall be calculated from the equation below. Prior to measurement, both lead terminals must be short-circuited for a minimum of 30 minutes. The lead terminal connected to the metal can case is connected to the negative side of the power supply.



Self-Discharge Characteristic (0H - 5.5 V Products)

The self-discharge characteristic is measured by charging a voltage of 5.0 VDC (charge protection resistance: 0 Ω) according to the capacitor polarity for 24 hours, then releasing between the pins for 24 hours and measuring the pin-to-pin voltage. The test should be carried out in an environment with an ambient temperature of 25° C or below and relative humidity of 70% RH or below. The soldering is checked.

4. Dismantling

There is a small amount of electrolyte stored within the capacitor. Do not attempt to dismantle as direct skin contact with the electrolyte will cause burning. This product should be treated as industrial waste and not is not to be disposed of by fire.



Notes on Using Supercapacitors or Electric Double-Layer Capacitors (EDLCs)

1. Circuitry Design

1.1 Useful life

The FC Series Supercapacitor (EDLC) uses an electrolyte in a sealed container. Water in the electrolyte can evaporate while in use over long periods of time at high temperatures, thus reducing electrostatic capacity which in turn will create greater internal resistance. The characteristics of the supercapacitor can vary greatly depending on the environment in which it is used. Basic breakdown mode is an open mode due to increased internal resistance.

1.2 Fail rate in the field

Based on field data, the fail rate is calculated at approximately 0.006 Fit. We estimate that unreported failures are ten times this amount. Therefore, we assume that the fail rate is below 0.06 Fit.

1.3 Exceeding maximum usable voltage

Performance may be compromised and in some cases leakage or damage may occur if applied voltage exceeds maximum working voltage.

1.4 Use of capacitor as a smoothing capacitor (ripple absorption)

As supercapacitors contain a high level of internal resistance, they are not recommended for use as smoothing capacitors in electrical circuits. Performance may be compromised and, in some cases, leakage or damage may occur if a supercapacitor is used in ripple absorption.

1.5 Series connections

As applied voltage balance to each supercapacitor is lost when used in series connection, excess voltage may be applied to some supercapacitors, which will not only negatively affect its performance but may also cause leakage and/or damage. Allow ample margin for maximum voltage or attach a circuit for applying equal voltage to each supercapacitor (partial pressure resistor/voltage divider) when using supercapacitors in series connection. Also, arrange supercapacitors so that the temperature between each capacitor will not vary.

1.6 Case Polarity

The supercapacitor is manufactured so that the terminal on the outer case is negative (-). Align the (-) symbol during use. Even though discharging has been carried out prior to shipping, any residual electrical charge may negatively affect other parts.

1.7 Use next to heat emitters

Useful life of the supercapacitor will be significantly affected if used near heat emitting items (coils, power transistors and posistors, etc.) where the supercapacitor itself may become heated.

1.8 Usage environment

This device cannot be used in any acidic, alkaline or similar type of environment.



Notes on Using Supercapacitors or Electric Double-Layer Capacitors (EDLCs) cont.

2. Mounting

2.1 Mounting onto a reflow furnace

Except for the FC series, it is not possible to mount this capacitor onto an IR / VPS reflow furnace. Do not immerse the capacitor into a soldering dip tank.

2.2 Flow soldering conditions

Keep solder under 260°C and soldering time to within 10 seconds when using the flow automatic soldering method. (Except for the FC and HV series)

2.3 Installation using a soldering iron

Care must be taken to prevent the soldering iron from touching other parts when soldering. Keep the tip of the soldering iron under 400°C and soldering time to within 3 seconds. Always make sure that the temperature of the tip is controlled. Internal capacitor resistance is likely to increase if the terminals are overheated.

2.4 Lead terminal processing

Do not attempt to bend or polish the capacitor terminals with sand paper, etc. Soldering may not be possible if the metallic plating is removed from the top of the terminals.

2.5 Cleaning, Coating, and Potting

Except for the FM series, cleaning, coating and potting must not be carried out. Consult KEMET if this type of procedure is necessary. Terminals should be dried at less than the maximum operating temperature after cleaning.

3. Storage

3.1 Temperature and humidity

Make sure that the supercapacitor is stored according to the following conditions: Temperature: $5 - 35^{\circ}$ C (Standard 25°C), Humidity: 20 - 70% (Standard: 50%). Do not allow the build up of condensation through sudden temperature change.

3.2 Environment conditions

Make sure there are no corrosive gasses such as sulfur dioxide, as penetration of the lead terminals is possible. Always store this item in an area with low dust and dirt levels. Make sure that the packaging will not be deformed through heavy loading, movement and/or knocks. Keep out of direct sunlight and away from radiation, static electricity and magnetic fields.

3.3 Maximum storage period

This item may be stored up to one year from the date of delivery if stored at the conditions stated above.